



Rubber BV, Oude Molenmeent 10-8, 1231 BD LOOSDRECHT

+31 35 6246615 info@rubberbv.nl www.rubberbv.nl

Technical data sheet Status: 01.06.2021

tubes, profiles

Vitonslang 2900

Pos	Parameter	Value	Unit	Norm
	Elastomer base	FKM		
	Geometry	Tube		
	Density	2,01	g/cm ³	ASTM D 297
	Hardness	70 +/-5	Shore A	ASTM D 2240
	Tensile strength	13,1	MPa	ASTM D 412
	Elongation at break	268	%	ASTM D 412
	Compression set	28 at 200 °C; 70 h	%	ASTM D 395 B2
	Temperature	-15 to +200	°C	
	Color	black		

Pos*	Compliant	Addition

Pos* A= Outside; IN= Inside, S1= Side1, S2= Side2

The values of these specifications come from regular controls of the compounds with the aid of norm samples and perform an average. They correspond to the actual state of the knowledge, the latest development of the sciences and our experience. They do not specify sure properties for the final products. The indications in this data sheet are only a description of the typical properties and represent an aid and information for the user to give him some suggestions for his own application. But it remains in his responsibility to make sure with a specific trial that our product suits for his own purpose.

We strive to continuously improve our products. We reserve the right to modify and adjust the data sheet and our blends referring to the material properties. These will be documented with a new change status (date).